

# **STRUCTURAL RELIABILITY OF WOOD AND COMPOSITE POLES SUBJECT TO HURRICANE WINDS**

\*Sriram Kalaga<sup>1</sup>, Scott Holmes<sup>2</sup> and Galen Fecht<sup>2</sup> <sup>1</sup>602 North Shore Drive Glen Burnie, Maryland, MD 21060, USA <sup>2</sup>RS Technologies, Calgary, Alberta, Canada

#### **ABSTRACT**

In this study, the structural reliability of wood and composite distribution poles in hurricane wind environments is investigated. Numerical values of reliabilities of ten selected poles ranging from 10.7 to 16.7 m (35 ft. to 55 ft.), with standard embedment, are computed and compared. Applied loads correspond to a typical, 4-wire distribution pole subject to 210 kmph (130 mph) wind. Though preliminary, this study showed that composite poles can offer more than twenty times the reliability of wood poles for the high-wind loading considered. Based on results of this study composite poles are deemed ideal for pole replacement in hurricane-prone areas and to meet the additional demand for resilience and reliability.

**Keywords**: Composite, distribution, modular, poles, polymer, reliability, wood.

# **INTRODUCTION**

Hurricanes, tornadoes, and ice storms cause substantial damage to overhead utility lines every year requiring emergency system restoration and rebuilding. This system rebuilding process is often aimed at *hardening* or strengthening of the electrical power infrastructure to prevent future damage and reduce or eliminate outages due to structural failures.

Wood, steel, lattice, concrete, laminated wood and composite (FRP or fiber-reinforced polymer) currently comprise the materials used in transmission and distribution structural systems. Among these, wood is the dominant choice of material in nearly 95% of distribution lines (ANL, 2016). Each year at least 3.6 million damaged or failed wood poles are replaced while 1.9 million new poles are installed (Kalaga, 2013). Also, each year due to weather events and loss from age, rot, and decay an average of 2.5 million of the roughly 130 million wood poles in service need to be replaced (Coughlin, 2018).

Composite poles are currently becoming increasingly popular in the utility industry at both transmission and distribution levels. The advantages they offer include established engineered performance, light weight, great flexural strength, ease of installation, safe against almost all weather-related effects, excellent fire resistance, and finally, an estimated maintenance-free service life of nearly 80 years.

\_

A review of literature shows that most research on utility poles – both analytical and experimental – is focused on determining pole strength under various load conditions. Previous reliability studies (Kalaga, 2022) dealt with assessing probability of failure under standard or test loads. There is little information available on evaluating and comparing the actual structural reliabilities of wood and composite poles in a *hurricane or high-wind loading environment*. Such a quantitative assessment will be helpful to utility owners in planning for pole replacements after a climactic event. The present study is a small step towards that goal and is focused on comparing reliabilities of WRC (Western Red Cedar) wood and filament-wound, modular composite poles when subject to extreme wind loads. Only tangent distribution–size poles (voltages under 46 kV) with pole lengths ranging from 10.7 (35 ft.) to 16.7 m (55 ft.) are considered. All poles are directly embedded into the ground to a depth of 10% of pole length plus 0.6 m  $(2 \text{ ft.})$ .

#### **MATERIALS AND METHODS**

### POLE MATERIAL DATA

## **Western Red Cedar Wood Poles**

- 1. Designated fiber bending strength (or Modulus of Rupture, MOR) of 41.4 MPa (6,000 psi).
- 2. Modulus of Elasticity (MOE) is 10.96 GPa (1,590 ksi)
- 3. Design is governed by bending at the ground line.

<sup>\*</sup>Corresponding author e-mail: drkalaga@hotmail.com

Note that the MOR is a *mean* value with an *average* coefficient of variation (COV) of 0.20 corresponding to ANSI data for all un-guyed poles (ANSI, 2017). Wood is also a bio-degradable material, and therefore from a structural perspective, strength reduction factors are specified for design to account for the statistical variation, decay and decrease of wood strength with time (RUS, 2015; USDA, 2001).

For extreme wind loads, current guidelines (NESC, 2017) specify a strength reduction factor of 0.75 for all wood structures.

## **Modular Composite Poles**

RS Technologies Inc.'s (RS Tech, 2012) filament-wound FRP poles are used in this study.

- 1. Fiber (bending) strengths range from 125 MPa (18.17 ksi) to 288.5 MPa (41.87 ksi) depending on the module and wall thickness.
- 2. Modulus of Elasticity (MOE) usually varies from 16.7 GPa (2,422 ksi) to 24 GPa (3,481 ksi) depending on module.
- 3. Design is governed by strength (flexural capacity or bending stress) at the ground line.

For extreme wind loads, current guidelines (NESC, 2017) specify a strength factor of 1.0 for all composite structures.

## **Reliability of utility structures**

Design of transmission and distribution structures in North America is based on Load and Resistance Factor Design or LRFD approach (ASCE, 2019; NESC, 2017; RUS, 2015; CAS, 2015). This approach matches the statistical variability of imposed loads with the variability of structural resistance to help reduce the potential for failure. It is also known as Reliability-Based Analysis and Design (RBAD) as it provides a known level of design reliability based on the Return Period (RP) or Mean Recurrence Interval (MRI) of climactic events such as hurricanes and ice storms. The current default MRI is 100 years (ASCE, 2019), although larger periods of 200 years and above are often used in special circumstances.

Table 1 shows a typical relationship between Reliability Index *β* and Probability of Failure  $P_f$ . Engineers often choose a design target of  $\beta = 3.0$  which translates to a failure probability of roughly 1.4 poles out of 1000 poles.

The basic principles of structural reliability, applied loads, resistances, and associated equations are given in Appendix 1.

The reader is referred to the literature available on the topic (Ang and Tang, 1984; Kharmanda, 2016) for more information on the various loading criteria and individual structural element resistance related to RBAD. ASCE Manual of Practice 111 (ASCE, 2006) gives the general requirements of reliability for utility pole structures. Guidelines governing the performance of composite utility pole structures are given in the ASCE Manual of Practice 104 (ASCE, 2019).

### **Reliability assessment of selected poles**

The reliability concepts of Appendix 1 are applied to a selected set of five (5) wood and five (5) equivalent modular composite poles and their performance is assessed in terms of probabilistic resistance and applied loads. See Figure 1 for geometry of poles used in this study as well as ANSI definition of pole strength in terms of a single lateral (cantilever) load applied 0.6 m (2 ft.) below pole top.

For simplicity, resistance variables are assumed to be normally distributed. The following coefficients of variations (COV) are used:

Wood  $COV_R = 0.20$  applied to the maximum bending stress or MOR (ANSI, 2017)

Composite  $COV_R = 0.05$  applied to the maximum flexural stress in the material (ASCE, 2019)

Applied Load Effects  $COV<sub>W</sub> = 0.09$  applied to the wind load

Wind loads generally follow a Weibull or other Extreme Value distribution but for simplicity are assumed to be normally distributed for this paper. The COV for wind pressure (0.09) is taken from an average of those suggested Joffre and Laurila (1988) and NCHRP (2003).

The selected sets of poles and their load ratings are shown in Table 2 (wood) and Table 3 (composite). The poles cover a length range of  $10.7$  to  $16.7$  m  $(35$  ft. to  $55$  ft.) common in distribution applications. The filament-wound composite poles correspond to the wood equivalents obtained from the Pole Selector algorithm of RS Poles (RS Tech, 2015).

Factored load ratings of wood poles of Table 2 include a strength reduction factor of 0.75 mandated by NESC for extreme wind (Rule 250-C) loads. The composite pole load ratings of Table 3 are based on RS Poles Technical Binder (RS Tech, 2012) and are calibrated on the basis of testing. The ground line moment capacity of composite poles is roughly based on these load ratings. The strength factor used for composite poles is 1.00, per NESC.



Table 1. Typical Variation of  $P_f$  with Beta.

Table 2. Selected Wood Poles: Lengths, Load Ratings and Weights.



<sup>a</sup> Applied 0.6 m from the tip of the pole

<sup>b</sup> with 0.75 strength (reduction) factor

\* All poles are ANSI Class 1

Table 3. Selected Composite Poles: Lengths, Load Ratings and Weights.



<sup>a</sup> Applied 0.6 m from the tip of the pole

**b** Based on RS Technologies Design Binder [RS Tech, 2012]

**\*\*** based on RS Pole Selector [RS Tech, 2015]

Table 4.Wood Poles: Geometric and Strength Data \*

Wood	Pole	Embed	<b>Height Above</b> Ground $L_{AG}$	<b>GL</b> Diameter $d_{gl}(mm)$	Moment	Section	Moment
Pole	Length L	$D_e(m)$			of Inertia I $(x$	Modulus $S(x)$	Capacity
No.	(m)		(m)		$10^8 \text{mm}^4$ )	$10^6$ mm <sup>3</sup> )	$M_R$ (kN-m)
	10.7	1.8	8.9	343.7	6.84	3.98	165
	12.2	1.8	10.4	363.7	8.60	4.73	196
	13.7	2.0	1.7	382.0	10.44	5.47	226
	15.2	2.1	13.1	396.0	12.08	6.10	252
	16.7	2.3	4.4	410.0	13.91	6.78	281

\* All Poles are ANSI Class 1, Western Red Cedar (MOR = 41.4 MPa)

Composite Pole No.	Pole Length L(m)	Embed $D_e(m)$	Length $L_{AG}$ (m)	GL Diameter $d_{gl}(mm)$	GL	Module	Moment	Section	Moment
					Module	Flexural	of Inertia	Modulus	Capacity
					Thickness	Strength $*$	I(x10 <sup>8</sup> )	S(x10 <sup>6</sup> )	$M_R$ (kN-
					$'t'$ (mm)	$f_m(MPa)$	$mm4$ )	$mm3$ )	m)
	10.7	1.8	8.8	427	9.7	205.2	2.96	1.385	284
	12.2	1.8	10.4	427	9.7	205.2	2.96	1.385	284
	13.7	2.0	11.7	500	9.7	199.3	4.74	1.896	378
	15.2	2.1	13.1	497	10.3	199.3	4.96	1.999	399
	16.7	2.3	14.4	494	10.3	199.3	4.87	1.974	394

Table 5. Composite Poles Geometric and Strength Data.

\* based on module at Ground Line GL

Table 6. Reliability Analysis of Wood Poles.

Wood Pole No.	Pole Height Above Ground $L_{AG}(m)$	Moment Capacity $M_R$ (kN-m)	Wind Load $P_A(kN)$	Applied Moment Std. Dev. $\sigma_R$ $M_W(kN-m)$	$(kN-m)$	Std. Dev. $\sigma_{W}$ $(kN-m)$	Reliability Index $\beta$
	8.8	165	19.3	159	24.7	14.2	0.220
2	10.4	196	19.3	188	29.3	17.0	0.228
B	11.7	226	19.3	214	33.9	19.3	0.306
4	13.1	252	19.3	241	37.9	21.7	0.267
5	14.4	281	19.3	267	42.1	24.0	0.277
						Average	0.260

Table 7. Reliability Analysis of Composite Poles.



The applied lateral load P<sup>A</sup> is the wind load on wires computed using the process shown in Appendix 2 and corresponding to the pole and 91.4 m (300 ft.) span wire configuration shown in Figure 2. Effect of wind on pole is excluded.

Tables 4 and Table 5 shows the calculated geometric data of the selected poles, along with the moment capacity (resistance) based on elastic material properties. All geometric properties refer to the ground line (GL). The wood data refers to ANSI and those of composite poles refer to the datasheets in the RS Poles Technical Binder. Section properties for modular poles are computed using tubular, thin-walled cross section equations available in literature (ASCE, 2012).

#### **RESULTS AND DISCUSSION**

Table 6 and Table 7 shows the reliability calculations for wood and composite poles, respectively. Composite poles consistently showed larger reliability indices. The low reliability of wood poles is attributed to the reduced (factored) resistance, large COV for wood properties (0.20) coupled with a high COV of wind loads (0.09). In comparison, the composite poles have no strength reduction and little variation in elastic parameters. The average reliability index  $β$  for composite poles is 5.222 whereas that for the wood poles is 0.260. That is, composite poles are more than twenty times safer than wood poles at the hurricane load levels indicated. In terms of probabilities of failure, this translates to the following values (see Table 1):



Fig. 1. Wood and Composite Poles: Geometrical Configuration.

Composite: Probability of Failure P<sub>f</sub> for  $\beta = 5.222$  is less than 0.000001

Wood: Probability of Failure P<sub>f</sub> for  $β = 0.260$  is 0.398

Numerically, this means that for every 1000 poles subject to 210 kmph (130 mph) wind loads, wood poles would experience nearly 400 failures whereas composite poles would experience virtually no failures at all.

If one were to reverse-calculate the wood pole class required to sustain the imposed hurricane wind loads, using Equation (A-1) for computing M<sub>R</sub> for a β of 3.0, it can be seen that Class H5 is needed for 13.7 m (45 ft.) and 15.2 m (50 ft.) poles. (Class H5 is not available for lengths lower than 13.7 m). Class H5 wood poles would also mean 60% heavier poles compared to composites.

# **CONCLUSIONS**

In this study, we investigated the structural reliability of modular composite poles in comparison with Western Red

Cedar wood poles. Pole lengths ranged from 10.7 m to 16.7 m (35 ft. to 55 ft.]. All wood poles are of Class 1. Applied loads corresponded to a typical distribution pole with 4 wires (3 phases and 1 neutral) with a wind span of 91.4 m (300 ft.). Wind pressure corresponded to 210 kmph (130 mph) wind velocity.

Major inferences from reliability analyses of the 10 (ten) poles studied here include:

- 1. Composite poles showed significantly higher structural reliability than wood poles.
- 2. The computed average reliability index of composite poles (5.222) is more than twenty times the corresponding average of wood poles (0.260).
- 3. From a weight-versus-reliability perspective, composite poles are 60% lighter than wood which translates into large savings in transportation costs.
- 4. Given the low probabilities of failure, composite poles are ideally suited for hurricane-prone areas as a oneon-one replacement for wood poles or as a strategic alternative to wood poles.



Fig. 2. Scheme for Calculation of Wind Load on Poles.

This investigation used Western Red Cedar (WRC) wood poles, but the results are also considered valid and applicable to other types of wood. To complement this study, reliabilities at other climactic loads involving ice and wind (such as NESC District Loads 250-B and 250-D), can be studied in the future. Deflections of poles are not considered here; but if proper definitions of service loads and/or deflection limits, are available, future editions of this study may assess reliabilities subject to such limits.

#### **Appendix 1: Reliability Principles**

The traditional definition of a Reliability Index for a *normally distributed variable* is:

$$
\beta = M_R - M_W / \sqrt{sqrt(\sigma_R^2 + \sigma_W^2)}
$$
 (A-1)

where:

 $M_R$  = Mean value of Resistance at GL determined from A-2 or A-3

 $M_W$  = Mean Value of Applied Load Effects at GL =  $(P_A) * (L_{AG} - 0.6)$ 

 $P_A$  = See Appendix 2 below

 $L_{AG}$  = Pole Height Above Ground

 $\sigma_R$  = Standard Deviation of Resistance = (COV<sub>R</sub>) \* ( $M_R$ )

 $\sigma_W$  = Standard Deviation of Load Effect = (COV<sub>W</sub>) \* ( $M_W$ )

 $COV_R = Coefficient of Variation of Resistance$ 

 $COV<sub>W</sub> = Coefficient of Variation of Load Effect$ 

For circular wood cross sections:  $M_R = (S) * (MOR) = (\pi * d_{gl}^3 / 32) * (MOR)$ (A-2) S = Section Modulus

 $d_{al}$  Pole Diameter at GL

MOR = Modulus of Rupture or Wood Fiber Strength

For tubular composite (FRP) cross sections:  
\n
$$
M_R = (S) * (f_m) = (0.786 * d_{gl}^2 * t) * (f_m)
$$
\n(A-3)

 $S = Section Modulus$ 

 $d_{al}$  = Pole Diameter at GL

 $t =$  pole module thickness at GL

 $f_m$  = Flexural Strength of the pole module at the GL

# **Appendix 2: Calculation of Applied Wind Loads P<sup>A</sup>**

Effective span =  $91.44$  m (300 ft.) Number of conductors  $= 4$  (3 phase, 1 Neutral) Diameter of the conductor =  $25 \text{ mm} (1")$ 

Wind speed  $V = 210$  kmph (130 mph)

Wind pressure  $w = 0.00256$   $V^2 = (0.00256)(130)(130) =$ 43.3 psf (2.07 kPa)

Wind force acting on pole  $P_A = (4)(300)(1/12)(43.3) =$ 4330 lbs. (19.3 kN)

Moment  $M_W$  due to Applied Load  $P_A$  is calculated using Equation A-3.

#### **ACKNOWLEDGMENT**

Financial support provided by the R&D Division of RS Technologies, Inc., Calgary, Alberta, Canada is gratefully acknowledged. The authors are also grateful for the input and suggestions from the engineering and manufacturing staff of RS Technologies, Inc.

#### **REFERENCES**

ASCE. 2019. American Society of Civil Engineers Manual of Practice 74. Guidelines for Electrical Transmission Line Structural Loading (4<sup>th</sup> edi.). Reston, VA, USA.

ASCE. 2019. American Society of Civil Engineers Manual of Practice 104. Recommended Practice for Fiber-Reinforced Polymer Products for Overhead Utility Line Structures (2nd edi.). Reston, VA, USA.

ASCE. 2006. American Society of Civil Engineers Manual of Practice 111. Reliability-Based Design of Utility Pole Structures. Reston, VA, USA.

ASCE. 2012. American Society of Civil Engineers. Standard 48-11. Design of Steel Transmission Pole Structures. Reston, VA, USA.

Ang, AHS. and Tang, WH. 1984. Probability Concepts in Engineering Planning and Design. John Wiley and Sons, New York, NY, USA.

ANL. 2016. Argonne National Laboratory. National Electricity Emergency Response Capabilities. Report prepared for US Department of Energy. Washington, DC, USA.

ANSI. 2017. American National Standards Institute, American National Standard for Wood Poles – Specifications and Dimensions. ANSI Standard O5-1. New York, NY, USA.

CSA. 2015. Canadian Standards for Overhead Systems, CSA-C22.3 1-15. Canadian Standards Association. Mississauga, Ontario, Canada.

Coughlin, D. 2018. Weathering the Weather: The Benefits of Composite Utility Poles in Storm Zones. Electric Energy T&D magazine July/August. Jaguar Expo Inc., Quebec, Canada.

Joffre, SM. and Laurila, T. 1988. Standard Deviations of Wind Speed and Direction from Observations Over a Smooth Surface. Journal of Applied Meteorology. 27(5): 550-561.

Kalaga, S. 2013. Composite Transmission and Distribution Poles: A New Trend, On-Line Publication, Transmission Professionals Group, Energy Central Grid Network.

Kalaga, S. 2022. Reliability Assessment of Filament-Wound Composite Transmission and Distribution Poles. Report RS-SK-22-01 (In press to RS Technologies).

Kalaga, S. 2022. Reliability Assessment of Transmission Poles. European Journal of Engineering Technology and Research. 17(5):76-81.

Kharmanda, G. and El-Hami, A. 2016. Reliability in Biomechanics. (1<sup>st</sup> edi.). John Wiley and Sons. New York, NY, USA.

NESC. 2017. National Electrical Safety Code ANSI C-2- 17. Institute of Electrical and Electronics Engineers. New York, NY, USA.

NCHRP. 2003. Report 489, Design of Highway Bridges for Extreme Events. Transportation Research Board, Washington, DC, USA.

RS Technologies. 2012. RS Standard Modular Composite Utility Poles: Technical Binder. Calgary, Alberta, Canada.

RS Technologies. 2015. RS Pole Selector. Internal Design Aid, RS Technologies, Calgary, Alberta, Canada.

RUS. 2015. Rural Utilities Services. Design Manual for High Voltage Transmission Lines. Bulletin 1724E-200. United States Department of Agriculture (USDA), Washington, DC, USA.

USDA. 2001. United States Department of Agriculture, Derivation of Nominal Strength for Wood Utility Poles. General Technical Report FPL-GTR-128. Washington, DC, USA.

> Received: August 29, 2023; Revised: Sept 16, 2023; Accepted: Sept 23, 2023

Copyright©2023 Kalaga *et al*. This is an open access article distributed under the Creative Commons Attribution Non Commercial License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

